



Shieldex[®] Bremen PW

1100201130

Shielding effectiveness 0.2 - 14 GHz according to IEEE 299/2006





Shieldex[®] Bremen PW

1100201130



Raw Material	100 % Polyamide / Nylon 6.6
Weave	Plain weave
Thread density warp	≈ 480-500 threads/dm
Thread density weft	≈ 460-480 threads/dm
Metal Plated	99.9 % Pure Silver
Metal Content	18.60 ± 2 % Silver
Electrical Surface Resistivity	< 0.3 Ω/□
Measured Frequency	0.2 GHz – 14 GHz
Shielding Effectiveness 1	Average of < 63 dB from 0.2 GHz – 2 GHz
Shielding Effectiveness 2	Average of < 63 dB from 2 GHz – 5 GHz
Shielding Effectiveness 3	Average of < 67 dB from 5 GHz – 14 GHz
Total Weight	43 g/m ² ± 10 %
Total Thickness	0.06 mm ± 12 %
Roll Width	130 ± 3 cm
Roll Length	Average 100 m
Temperature Range	-30 °C to 90 °C
Storage and Handling	According to our care and handling instructions
Compliance and Certification	DIN EN ISO 9001:2015, REACH, RoHS

Alterations Reserved 01.05.21/03 – The above information has been compiled from our manufacturer area according to the latest state of development and application technology. Since application and further processing are beyond our control, no liability of the producer can be derived from the contents of the data sheet. All deviant or transcending data sheet information must be confirmed in written form by the manufacturer. Our general terms and conditions apply in all cases. All previous data sheets are invalid with the publication of this data sheet. Please note our handling and storage instructions as well accessible at www.shieldex.de.